

Fire-Rated, Forced Entry and Bullet Resistant Transparent Wall Panel for Schools and Education Facilities
Fire-Rating: Up to 120 Minutes

Pilkington Pyrostop® School Guard Glass® is fire rated for up to 120 minutes, offers a Level III bullet resistance rating and withstands forced entry attacks in standard fire doors.

FEATURES

- Deters forced entry in Fireframes® doors and frames from TGP and compliant doors and frames for 12+ minutes
- Meets ASTM F1233 class 1.4 and H.P. White 5-aa1 for 12:10
- Bullet resistance ratings up to UL Level III (up to Level VIII available in different make-ups)
- Protection against radiant and conductive heat transfer
- Barrier to fire and smoke
- Impact safety-rated-meets ANSI Z97.1 and CPSC 16 CFR1201 (Cat. I and II)
- Wireless with nearly the same clarity as ordinary float glass
- For use in interior and exterior applications
- Available incorporating a variety of glass products, including (but not limited to): Tinted; One-Way Mirror; Low-E; Reflective; Art Glass; Translucent Interlayer (for added obscurity and privacy)
- Fits in Fireframes® Heat Barrier Series by TGP
- Available for use in compliant frames by others (see frame manufacturer for details)
- Multi-laminate, not a sensitive polymer unit

Pilkington Pyrostop sales are a cooperative effort between Technical Glass Products and Pilkington North America.

LISTINGS / STANDARDS

Classified and labeled by Underwriters Laboratories, Inc.® and Underwriters Laboratories of Canada. File number for labeled fire-rated assemblies is R13377 (45 minutes) and R38725 (60-120 minutes). Tests performed in accordance with:

UL 9	NFPA 80	CAN4 S-104	ASTM E119	MEA 290-90-M-6	HPW 5-aa1
UL 10B	NFPA 251	CAN4 S-106	ASTM F1233	LARR 25798	
UL 10C	NFPA 252	CAN/ULC-S101			
UL 263	NFPA 257				
UL 752					
UL 972					

LABELING

Each piece of Pilkington Pyrostop shall be permanently labeled with the Pilkington Pyrostop logo, UL logo and fire rating.

STORAGE & HANDLING

Pilkington Pyrostop must be handled with care during transportation, storage, inspection and installation. It should be stored in dry conditions, stocked vertically and fully supported in a manner which prevents the glass from sagging. During storage and transportation, the temperature of Pilkington Pyrostop should not exceed 122°F (50°C). Do not expose the "non-PVB" side of the glass to UV light. Do not remove the protective edge tape. See manufacturer's installation and warranty information for further details.

INSTALLATION

If either dimension exceeds 84" or if the unit exceeds 34 ft², the Pilkington Pyrostop School Guard Glass thickness will increase by 1/8", thus increasing the unit thickness by 1/8".

Only Kerafix® is approved for use with Pilkington Pyrostop School Guard Glass.



BIM 3D Model Available



UL Classified & Labeled



Fire-Rated



Hose Stream Tested



Impact-Rated



Heat Barrier



Positive Pressure Tested



Bullet Resistant



Forced Entry Resistant

UL-752 BULLET RESISTANCE

UL-752 BULLET RESISTANCE RATING	FIRE RATING	PILKINGTON PYROSTOP DESIGNATION	SUPPLY FORM	NOMINAL THICKNESS	WEIGHT APPROX.	ASSEMBLY	MAX. EXPOSED AREA	MAX. WIDTH OF EXPOSED GLAZING	OR	MAX. HEIGHT OF EXPOSED GLAZING
Level I	60 min.	60-201 (with film**)	Single Glazing	1-1/16" (27 mm)	12.90 lbs/ft ² (63.00 kg/m ²)	OTHER THAN DOORS DOOR	7,442 in ² (4.80 m ²) 3,724 in ² (2.40 m ²)	96" (2.44 m) 41-5/8" (1.06 m)		118-1/8" (3.00 m) 89-3/4" (2.28 m)
Level II	120 min.	120-201**	I.G. Units	2-7/16" (62 mm)	25.81 lbs/ft ² (126.00 kg/m ²)	OTHER THAN DOORS	3,724 in ² (2.40 m ²)	111" (2.81 m)		111" (2.81 m)
Level III	120 min.	120-201 (with film**)	I.G. Units	2-7/16" (62 mm)	25.81 lbs/ft ² (126.00 kg/m ²)	OTHER THAN DOORS	3,724 in ² (2.40 m ²)	111" (2.81 m)		111" (2.81 m)
Level II	120 min.	120-202 (with film*)	Single Glazing	1-9/16" (41 mm)	18.64 lbs/ft ² (91.00 kg/m ²)	OTHER THAN DOORS DOOR	3,724 in ² (2.40 m ²) 3,724 in ² (2.40 m ²)	111" (2.81 m) 41-5/8" (1.06 m)		111" (2.81 m) 89-3/4" (2.28 m)

*For filmed products, one dimension of the glass cannot exceed 60" (1.52 m)

+ Available with a translucent interlayer

^ Interior use only

FOR APPROVED FRAMING SYSTEMS FOR USE WITH PILKINGTON PYROSTOP, VISIT FIREGLASS.COM OR CALL 800.426.0279

SCHOOL GUARD GLASS ASTM F1233 AND HPW 5-aa1

FIRE RATING	PILKINGTON PYROSTOP DESIGNATION	SUPPLY FORM	NOMINAL THICKNESS	WEIGHT APPROX.	ASSEMBLY	MAX. EXPOSED AREA	MAX. WIDTH OF EXPOSED GLAZING	OR	MAX. HEIGHT OF EXPOSED GLAZING
45 min.	45-200	Single Glazing	1.25" (32 mm)	13.82 lbs/ft ² (67.46 kg/m ²)	OTHER THAN DOORS DOOR	4,500 in ² (2.90 m ²) 3,724 in ² (2.40 m ²)	95-1/4" (2.42 m) 41-5/8" (1.06 m)		95-1/4" (2.42 m) 89-3/4" (2.28 m)
60 min.	60-101^	Single Glazing	1.41" (36 mm)	15.46 lbs/ft ² (75.46 kg/m ²)	OTHER THAN DOORS DOOR	5,616 in ² (3.62 m ²) 3,724 in ² (2.40 m ²)	96" (2.44 m) 41-5/8" (1.06 m)		96" (2.44 m) 89-3/4" (2.28 m)
60 min.	60-201*	Single Glazing	1.57" (40 mm)	17.50 lbs/ft ² (85.46 kg/m ²)	OTHER THAN DOORS DOOR	7,442 in ² (4.80 m ²) 3,724 in ² (2.40 m ²)	96" (2.44 m) 41-5/8" (1.06 m)		118-1/8" (3.00 m) 89-3/4" (2.28 m)
90 min.	90-102^	Single Glazing	1.96" (50 mm)	22.21 lbs/ft ² (108.46 kg/m ²)	OTHER THAN DOORS DOOR	3,724 in ² (2.40 m ²) 3,724 in ² (2.40 m ²)	96" (2.44 m) 41-5/8" (1.06 m)		96" (2.44 m) 89-3/4" (2.28 m)
120 min.	120-104^	I.G. Units	2.63" (67 mm)	26.31 lbs/ft ² (128.46 kg/m ²)	OTHER THAN DOORS	3,730 in ² (2.41 m ²)	111" (2.81 m)		111" (2.81 m)
90 - 120 min.	120-202	Single Glazing	2.87" (73 mm)	23.24 lbs/ft ² (113.47 kg/m ²)	OTHER THAN DOORS DOOR	3,730 in ² (2.41 m ²) 3,724 in ² (2.40 m ²)	111" (2.81 m) 41-5/8" (1.06 m)		111" (2.81 m) 89-3/4" (2.28 m)
120 min.	120-262	I.G. Units	2.87" (73 mm)	26.31 lbs/ft ² (128.46 kg/m ²)	OTHER THAN DOORS	3,730 in ² (2.41 m ²)	111" (2.81 m)		111" (2.81 m)

Note: Both Pilkington Pyrostop and School Guard Glass have a ± 1/16" tolerance giving an overall thickness tolerance of ± 1/8"

+ Available with a translucent interlayer

^ Interior use only